



Precision-V 372DA Vapor-Degreaser Solvent Product# 372DA

Product Description

Techspray® has formulated Precision-V 372DA to be a drop-in replacement for 3M Novec 72DA.

Precision-V cleaners leave no residue and evaporate extremely fast, and are nonflammable with no flash-point. Electronics, optics, and metal parts are quickly and thoroughly cleaned, eliminating the need for further rinsing. Precision-V is non-ozone depleting, so ideal replacements for cleaners containing Freon, HFC-141b and AK225.

Precision-V 372DA has azeotrope properties that allow it to maintain stable properties as it is cycled in a vapor-degreaser. It is neither reactive nor corrosive to metals commonly found in the construction of vapor-degreasers.

Exposure to Precision-V solvents is less hazardous than many other solvents commonly used in vapor-degreasers: e.g. TCE (Trichloroethylene, CAS #79-01-6), nPB (n-Propyl Bromide, CAS #106-94-5), and Perc (Perchloroethylene, CAS #127-18-4).

NOTE: As with all vapor degreaser equipment and processes, observe all safety precautions, guidelines and operating rules associated with these units. Failure to do so may put operations personnel at risk. Avoid excessive vapor losses, loss of refrigeration, excessive boil sump heat, etc. Make sure all equipment is operated in accordance with the manufacturer's guidelines and instructions. If in doubt, contact your manufacturer immediately.

Features / Benefits

- Drop-in replacement for 3M Novec 72DA
- Nonflammable
- Non-conductive
- Compatible with plastics
- Low toxicity
- Low global warming potential (GWP)
- Zero ozone depletion potential (ODP)
- Low surface tension for cleaning within tight areas



Typical Product Data and Physical Properties

Exposure Limit	>200 ppm
Physical State	Liquid
Odor	ethereal
Appearance	Clear, colorless liquid
Flash Point	none
Percent Volatile	100
Vapor Pressure	360 mmHg
Initial Boiling Point	109°F (43°C)
Density	1.28±0.03 (g/cm ³)
Dielectric Strength	20-35 kV
Surface Tension	18 dynes/cm
GWP	43
Heat of Vaporization	251 kJ/kg
Kinematic Viscosity	0.35 cSt
Specific Heat	1242 J/kg·K
Kauri-butanol Value	58 Kb
Ozone Depletion Potential	0
Shelf Life	5 years

Precision-V 372DA Vapor-Degreaser Solvent Product# 372DA

Applications

- Used in vapor-degreasers and general solvent cleaner
- Rinsing agent
- Deposition solvent
- Effectively removes soils such as light/medium oils, ionic soils, greases, silicones, fluoro silicones, flux and wax

Reclamation Process

The reclamation (ie. boil down) process utilizes the vapor-degreaser as a still to distill solvent from the dirty boil sump and allows you to reclaim and reuse this solvent.

When it is determined that the Boil Sump needs to be cleaned out, you should do the following things to boil down the solvent:

1. If you have a 2 sump vapor-degreaser, drain the rinse sump into a clean container for reuse. If you have a one-sump vapor-degreaser, drain the spray reservoir using the spray wand. This material should be collected in a clean container, so it can be reused.
2. Allow the solvent to continue to boil, and the vapors to condense, until such time as one of two things happens:
 - a. the High Temperature Control (HTC) trips and turns off the heat to the heating elements or b. the Liquid Level Control trips because the level in the Boil Sump is too low.
3. Drain the remaining solvent/soil mixture into a container that is labeled as Hazardous Waste. This material can be used in future "boil downs" to reclaim more of the solvent in the mixture.
4. Use the retained solvent (from step 1) to refill the vapor-degreaser and add whatever volume of solvent is necessary to completely fill the machine.

This process can be repeated as often as necessary, depending on the amount of usage of the vapor-degreaser and the amount of soil that is introduced into the vapor-degreaser.

When you "boil down", always put the solvent/soil mixture into the vapor-degreaser to reclaim additional amount of the solvent from this mixture.

Compatibility

Precision-V cleaners are generally compatible within normal operating conditions of vapor degreaser and with exposed materials normally found with the equipment. Specific plastic and elastomeric formulations vary with manufacturers; therefore, we recommend compatibility verification when required.

Material	Compatibility
Acrylics	Non-Compatible
ABS/Polycarbonate	Non-Compatible
Nylon	Excellent
PTFE	Excellent
Epoxy	Excellent
PEEK	Excellent
Silicones	Fair
Ceramics	Excellent
Metals	Excellent

Packaging and Availability

Precision-V Vapor-Degreaser Flux Remover available in the following sizes:

372DA-G	10 lbs.
372DA-5G	50 lbs.
372DA-54G	550 lbs.

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Resources

Techspray® products are supported by global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory